arXiv:cond-mat/9408028v1 8 Aug 1994

Abstract

Molecular exciton effects in the neutral and maximally doped C_{60} (C_{70}) are considered using a tight binding model with long-range Coulomb interactions and bond disorder. By comparing calculated and observed optical spectra, we conclude that relevant Coulomb parameters for the doped cases are about half of those of the neutral systems. The broadening of absorption peaks is well simulated by the bond disorder model.

Optical response of C_{60} and C_{70} fullerenes: Exciton and lattice fluctuation effects

Kikuo Harigaya and Shuji Abe

Fundamental Physics Section, Electrotechnical Laboratory,
Umezono, Tsukuba, Ibaraki 305, Japan

February 1, 2008

1 INTRODUCTION

Fullerenes have a hollow cage of carbons [1]. Its structure is formed with σ-bondings. The π-electron orbitals extend to the outside of the cage. As π-electrons are delocalized on the surface of fullerenes, the optical properties are similar to those of π-conjugated polymers [2]. Recently, we have applied the intermediate exciton formalism which was used in polymers [3], and have investigated relevant Coulomb parameters in order to understand the dispersions and oscillator strengths of the absorption spectra of the neutral C_{60} (C_{70}) [4, 5] and maximally doped systems [6, 7]. The purpose of this article is to review the main results published elsewhere [8, 9].

In the formalism [8], a tight binding model with a long-range Coulomb interaction and bond disorder has been used. The free electron part corresponds to the simple Hückel model with the mean hopping integral t; the presence of the dimerization is considered for the neutral C_{60} case, and the constant hopping is assumed for the other cases. The long-range Coulomb interaction is the Ohno expression: $W(r) = 1/\sqrt{(1/U)^2 + (r/r_0V)^2}$. Here, U is the onsite Coulomb strength, V is the long-range component, and r_0 is the average bond length. The bond disorder model with the Gaussian distribution of the hopping integral with a standard deviation $t_{\rm s}$ simulates the lattice fluctuation effects [10]. This gives rise to broadening of the absorption spectra. The model is solved by the Hartree-Fock approximation and the single excitation configuration interaction method. Optical spectra are obtained by using the dipole approximation. In the next two sections, we present the calculated spectra and compare them with experiments.

2 NEUTRAL C_{60} AND C_{70}

We discuss the calculated optical absorption spectra of C_{60} and C_{70}. C_{60} has high I_h symmetry, and C_{70} has lower D_{5h} symmetry. Figure 1(a) shows the spectrum of C_{60}, and Fig. 1(b) that of C_{70}. Parameters, $U = 4t$, $V = 2t$, $t_{\rm s} = 0.09t$, and $t = 1.8$eV, are

used. These parameters are determined so as to reproduce the experimental spectra as good as possible. Experimental data of molecules in solutions are taken from [4, 5], and are shown by thin lines. There are three main features in C_{60} absorption found around the energies 3.5eV, 4.7eV, and 5.6eV. In the case of C_{70}, we could say that several small peaks in the energy interval from 1.7eV to 3.6eV are originated from the 3.5eV feature of C_{60} after splitting. The 4.7eV and 5.6eV features of C_{60} overlap into the large feature present in the energy region larger than 3.6eV. The optical gap decreases from 3.1eV (C_{60}) to 1.7eV (C_{70}). These changes would be due to the symmetry reduction from the C_{60} soccer ball to the C_{70} rugby ball. There is a good agreement with experiments about the peak positions and relative oscillator strengths in the C_{60} case. The agreement is overall for C_{70}. There is a systematic deviation of the experimental curves from the theoretical ones at energies higher than 5.0eV due to the overlap of σ-electron excitations.

3 MAXIMALLY DOPED C_{60} AND C_{70}

Calculations are performed for C_{60}^{6-} and C_{70}^{6-} in order to look at molecular exciton effects in A_6C_{60} and A_6C_{70} solids (A = alkali metals). Results are shown in Figs. 2(a) and (b) with the experimental absorption [6] and the optical conductivity data obtained by the EELS studies [7]. We find that the parameter set, $U = 2t$, $V = 1t$, $t_s = 0.20t$, and $t = 2.0$eV, is relevant to both systems. For A_6C_{60}, two features around 1.2eV and 2.8eV are reasonably explained by the present calculation. The broadening is simulated well by the bond disorder. The disorder strength $t_s = 0.20t$ is about the twice as large as that of the neutral C_{60}. The broad feature in the energies higher than 3.6eV in the experiments might correspond to the two broad peaks around 4.4eV and 6.0eV of the calculation. In these energies, the agreement is not so good. The same fact has been seen in the neutral C_{60} case. Excitations which include σ-orbitals would mix in this energy region. This effect could be taken into account by using models with π- and σ-electrons. For A_6C_{70} shown in Fig. 2(b), we can assign that the features at 1.2eV, 2.6eV, and 4.6eV of the calculation correspond to the peaks at 1.0eV, 2.7eV, and 4.2eV of the experiment, respectively. Thus, we can explain the presence of three broad features observed by experiments.

4 DISCUSSION

We have mainly looked at Frenkel exciton effects in the neutral and maximally doped C_{60} (and C_{70}) molecules. The relevant Coulomb parameters for the optical spectra are $U \sim 2V \sim 4t$ for the neutral systems, and $U \sim 2V \sim 2t$ for A_6C_{60} and A_6C_{70} solids. In the Ohno potential, the dielectric screening of Coulomb interactions can be taken into account by assuming $U = U_0/\varepsilon_s$ and $V = V_0/\varepsilon_l$, where ε_s and ε_l are short- and long-range dielectric constants. The magnitude of the static dielectric constant increases by the factor about two upon doping: $\varepsilon_1(0) = 4.3$ in the neutral C_{60} and $\varepsilon_1(0) = 7.1$ in Rb_6C_{60}, and also $\varepsilon_1(0) = 4.0$ in the neutral C_{70} and $\varepsilon_1(0) = 8.0$ in Rb_6C_{70} [7]. This enhancement of dielectric constants reasonably accords with the decrease of U and V in the present calculations.

References

[1] H.W. Kroto, J.E. Fischer and D.E. Cox (eds.), The Fullerenes, Pergamon Press, Oxford, 1993.

[2] A.J. Heeger, S. Kivelson, J.R. Schrieffer and W.P. Su, Rev. Mod. Phys. 60 (1988) 781.

[3] S. Abe, J. Yu and W.P. Su, Phys. Rev. B 45 (1992) 8264.

[4] S.L. Ren, Y. Wang, A.M. Rao, E. McRae, J.M. Holden, T. Hager, K.A. Wang, W.T. Lee, H.F. Ni, J. Selegue and P.C. Eklund, Appl. Phys. Lett. 59 (1991) 2678.

[5] J.P. Hare, H.W. Kroto and R. Taylor, Chem. Phys. Lett. 177 (1991) 394.

[6] T. Pichler, M. Matus, J. Kürti and H. Kuzmany, Solid State Commun. 81 (1992) 859.

[7] E. Sohmen and J. Fink, Phys. Rev. B 47 (1993) 14532.

[8] K. Harigaya and S. Abe, Phys. Rev. B 49 (1994) 16746.

[9] K. Harigaya, Jpn. J. Appl. Phys. 33 (1994) in press.

[10] K. Harigaya, Phys. Rev. B 48 (1993) 2765.



Figure 1: Optical absorption spectra for (a) C_{60} and (b) C_{70}, shown in arbitrary units. The parameters in the Ohno potential are $U = 4t$ and $V = 2t$ ($t = 1.8$eV). Experimental data are shown by thin lines. They are taken from [4] for (a), and from [5] for (b).



Figure 2: Optical absorption spectra for (a) C_{60}^{6-} and (b) C_{70}^{6-}, shown in arbitrary units. The parameters in the Ohno potential are $U = 2t$ and $V = 1t$ ($t = 2.0$eV). Experimental data of maximally doped systems are taken from [6] (thin line) and [7] (dots) for (a), and from [7] (dots) for (b).